



AUXILIARY PRODUCTS FOR ACID COPPER PLATING



Commodity Name

HN-GW ACID COPPER ADDITIVE



Bath Composition and Working Conditions

Additive HN-GW

0.05 ~ 0.15 ml /L



Application and Advantage

- 1.It has good effect in solving the problems of dendritic deposits and scorch phenomenon.
- 2.It can improve the dispersive ability and covering power of bath solution to get brighter and better leveling deposits.
- 3.It will affect the brightness of deposits when adding too much additive.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852