



ZINC PLATING PASSIVATION PRODUCT



Commodity Name

HN-51 ZINC BLACK PASSIVATION PROCESS



Bath Composition and Working Conditions

HN-51A Zinc Plating Black Passivation Agent	90-150mL/L
HN-51B Zinc Plating Black Passivation Agent	80-120mL/L
pH Value	1.2-1.8
Temperature	18-35°C
Passivation Time	40-90sec
Agitation	Mechanical agitation



Application and Advantage

1. It will produce a layer of perfect bright black passivation.
2. The anti-corrosion and anti-thermal ability of the passivation film are very good, and the life circle is long.
3. The operation range of the solution is wide, and it is easy to operate.
4. It is suitable for all zinc plating layers.



★★★★★
广东高力集团
HIGHNIC GROUP

 **广东致卓精密金属科技有限公司**
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax: (86-757) 85768678 Tel: (86-757) 85728852