



ZINC PLATING PASSIVATION PRODUCT



Commodity Name

HN-52 ZINC PLATING BLUE PASSIVATION PROCESS



Bath Composition and Working Conditions

HN -52	20~25ml/L
Nitric Acid(98%)	10~11ml/L
Time	5~15 secretary
Temperature	Room temperature
Agitation	Air agitation or mechanical agitation



Application and Advantage

- 1.It can produce perfect and bright blue passivative film with good anti-corrosion ability.
- 2.Single supplement, it is easy to operate.
- 3.It is suitable for all zinc plating layers.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852