



# ZINC PLATING PASSIVATION PRODUCT



## Commodity Name

HN-53 ZINC PLATING BLUE PASSIVATION PROCESS



## Bath Composition and Working Conditions

HN -53	8~10g/L
Nitric acid(98%)	10~12ml/L
Time	5~15 secretary
Temperature	Room temperature
Agitation	Air agitation or mechanical agitation



## Application and Advantage

- 1.It will produce perfect and bright blue passivative film with good anti-corrosion ability.
- 2.Single supplement, it is easy to operate.
- 3.It is suitable for all zinc plating layers.



**广东高力集团**  
HIGHNIC GROUP



**广东致卓精密金属科技有限公司**  
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852