



# ZINC PLATING PASSIVATION PRODUCT



## Commodity Name

HN-ZWP ZINC PLATING WHITE PASSIVATION PROCESS



## Bath Composition and Working Conditions

HN-ZWP	50-80mL/L
Temperature	Room temperature
Time	5-8 min
Agitation	Air agitation or mechanical agitation



## Application and Advantage

1. It save chromium trioxide.
2. It is Good for environment protection.
3. The coating is quite beautiful and solid, with good anti-corrosion ability.



★★★★★  
**广东高力集团**  
HIGHNIC GROUP

 **广东致卓精密金属科技有限公司**  
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852