



ZINC PLATING TRIVALENT CHROMIUM PASSIVATION PRODUCT



Commodity Name

HN-65 ZINC PLATING TRIVALENT CHROMIUM WHITE PASSIVATOR



Bath Composition and Working Conditions

HN-65	60~100ml/L
Temperature	20~35°C
Passivation Time	30~60 secretary
pH Value	2.0-3.5
Agitation	Mechanical agitation or air agitation



Application and Advantage

- 1.The products are completely free of Cr6+, and meet the requirement for exporting to Europe, America, Japan, etc.
- 2.The white passivation appearance is similar to that of hexavalent chromium. The anti-corrosion ability is better in coordination with Sealing Agent.
- 3.It is suitable for all kinds of acid/alkaline zinc rack/barrel plating. It is used under room temperature.
- 4.The passivation solution can be used in a wide range of pH value, and is easy to operate and adjust.



★★★★★
广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852