



# ZINC PLATING TRIVALENT CHROMIUM PASSIVATION PRODUCT



## Commodity Name

HN-GR ZINC PLATING TRIVALENT CHROMIUM GREY PASSIVATION PROCESS



## Bath Composition and Working Conditions

HN-GR	120ml/L
Temperature	20~30°C
Passivation time	30~90 secretary
pH Value	0~2.0
Drying Temperature	60~80°C



## Application and Advantage

- 1.The products are completely free of Cr6+, and meet the requirement for exporting to Europe, America, Japan, etc.
- 2.It can produce a layer of off white or grey black passivative film on the zinc plating layer.
- 3.Suitable for rack plating or barrel plating production line.



★★★★★  
**广东高力集团**  
HIGHNIC GROUP

 **广东致卓精密金属科技有限公司**  
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax: (86-757) 85768678 Tel: (86-757) 85728852