



ZINC PLATING TRIVALENT CHROMIUM PASSIVATION PRODUCT



Commodity Name

HN-68D TRIVALENT CHROMIUM BLUE PASSIVATION PROCESS



Bath Composition and Working Conditions

HN-680	50-100mL/L
Temperature	25-35°C
pH Value	1.8-2.2
Passivation time	15-30sec
Agitation	Mechanical agitation or air agitation



Application and Advantage

- 1.The products are completely free of Cr6+, and meet the requirement for exporting to Europe, America, Japan, etc.
- 2.It is suitable for all kinds of acid/alkaline zinc rack/barrel plating. It is used under room temperature.
- 3.The passivation solution can be used in a long time; instead of changing the solution frequently what you need to do is to add the solution according to the consumption.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司

SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852