



ZINC PLATING TRIVALENT CHROMIUM PASSIVATION PRODUCT



Commodity Name

HN-69 TRIVALENT COLOR PASSIVATOR



Bath Composition and Working Conditions

HN-69	50~150mL/L
Temperature	20~65°C
Passivation time	20~70 secretary
pH value	1.8~3.0
Agitation	Mechanical agitation



Application and Advantage

- 1.The products are completely free of Cr6+, and meet the requirement for exporting to Europe, America, Japan, etc.
- 2.The corrosion- resistance ability of the color passive film is excellent, can pass above 100-hour neutral salt spray test.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852