



# ZINC PLATING SEALANT



## Commodity Name

HN-58 ZINC PLATING PASSIVATION SEALANT



## Bath Composition and Working Conditions

HN-58	40~100ml/L
Temperature	20~40°C
Passivation Time	5~12 secretary
pH Value	3.5~5.0
Drying Temperature	Warm air with 60-100°C(more than 10 minutes)



## Application and Advantage

1. It can be used under room temperature.
2. The appearance of components won't be affected after sealing.
3. Protection to all kinds of zinc passivation film.
4. It has Long life, low additives consumption and easy to maintenance and control.
5. The anti-corrosion can be improved 24 to 48 hours.



广东高力集团  
HIGHNIC GROUP



广东致卓精密金属科技有限公司  
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852