



ZINC PLATING SEALANT



Commodity Name

HN-63D TRANSPARENT SEALANT



Bath Composition and Working Conditions

HN -63D	20~50%
Diluting Agent	Pure water
Temperature	40~70°C
Sealing Time	90~130 secretary



Application and Advantage

- 1.HN-63D is an inorganic sealant which is solvent, transparent silicate.
- 2.The color of the passivative film will not change after sealing process.
The corrosion resistance is obviously improved.



★★★★★
广东高力集团
HIGHNIC GROUP

 **I.M.T.** 广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax: (86-757) 85768678 Tel: (86-757) 85728852