



ALUMINUM ALLOY ZINCATE



Commodity Name

HN-200 ALUMINUM CYANIDE-FREE ZINCATE



Bath Composition and Working Conditions

HN-200	180~500ml/L
Temperature	18~43℃
Time	20~120s
Zinc Content	8~22g/L



Application and Advantage

1. It is easy to operate and suitable for rack plating and barrel plating.
2. There is no cyanide.
3. It will form even and fine grained zinc layer on aluminum surface; have good adhesion after plating.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852