



COLORING SERIES



Commodity Name

HN-CB BLACKENING AGENT FOR COPPER



Bath Composition and Working Conditions

| | |
|------------------------|------------|
| Copper Sulfate | 8-15g/L |
| Pure Sulfuric Acid | 7-10ml/L |
| Blackening Agent HN-CB | 90-100ml/L |
| Temperature | 15-35°C |
| Time | 50-90s |
| pH Value | 1-2.5 |



Application and Advantage

1. It is suitable for copper and copper alloy oxidation of black color.
2. It has Good luster, smooth surface, good decoration.
3. There is good adhesion of coating.
4. It is easy to operate, low cost, and has strong stability.



★★★★★
广东高力集团
HIGHNIC GROUP

 **I.M.T.** 广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852