



ALUMINUM ALLOY/ ALUMINUM-WHEEL PRETREATMENT PRODUCT



Commodity Name

HN-120 ALUMINUM ALLOY ALKALI ETCH



Bath Composition and Working Conditions

HN-120	30~40g/L
Temperature	Room temperature
Time	15~60s



Application and Advantage

- 1.Remove oxide film and oil film from surface of parts, improve adhesion of subsequent process.
- 2.Stable speed of corroding and won't appear partial corrosion. It is especially suitable for light corrosion of aluminum parts.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852