



PRETREATMENT PRODUCTS FOR PLASTIC PLATING



Commodity Name

HN-732 ACTIVATOR



Bath Composition and Working Conditions

HN-732 Activator	6-15 ml/L
Stannous Chloride	3-5 g/L
Hydrochloric Acid (36%)	250-300 ml/L
Temperature	20-35°C
Time	2-6 minutes
Agitation	Slight mechanical agitation
Filtration	Recycle filtration with non-metal pump



Application and Advantage

1. Stable activating performance and long working life.
2. It can be used as catalyst in electroless nickel or electroless copper plating.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司

SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852