



PRETREATMENT PRODUCTS FOR PLASTIC PLATING



Commodity Name

HN-735 ACTIVATOR



Bath Composition and Working Conditions

HN-735 Activator	3~7ml/L
Tin Chloride	3~5g/L
Hydrochloric Acid(37%)	250~300mL/L
Temperature	20~35
Time	2~6 minutes
Agitation	Slightly mechanical agitation(non air agitation)



Application and Advantage

- 1.It is a high concentration activator for plastic plating.
- 2.It has very stable activation ability, and long life.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司

SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852