



PRETREATMENT PRODUCTS FOR PLASTIC PLATING



Commodity Name

HN-736 ACTIVATOR



Bath Composition and Working Conditions

HN-736 Activator	3-7 ml/L
Stannous Chloride	3-5 g/L
Hydrochloric Acid (36%)	250-300 ml/L
Temperature	20-35°C
Time	2-6 minutes
Agitation	Slight mechanical agitation
Filtration	Recycle filtration with non-metal Pump



Application and Advantage

1. It has stable activating performance and long working life.
2. It can be used as catalyst in electroless nickel or electroless copper plating.



★★★★★
广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司
SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Sales Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel : (86-757) 85728852