



PRETREATMENT PRODUCTS FOR PLASTIC PLATING



Commodity Name

HN-849 ACCELERATOR



Bath Composition and Working Conditions

HN-849 Accelerator	30~60g/L
Sulfuric Acid	20~30ml/L
Temperature	50~65
Time	2~5minutes
Agitatio	Proper mechanical agitation (non air agitation)



Application and Advantage

- 1.It is an accelerator specially designed for plastic plating.
- 2.High stability, it is good to gain even and fine electroless plating layer.



广东高力集团
HIGHNIC GROUP



广东致卓精密金属科技有限公司

SUR-PRECISION METAL TECHNOLOGY CO., LTD.

- Production Base : Central Part of Non-ferrous Metal Industrial Development Zone, Shishan, Nanhai, Foshan, Guangdong, China
- Slaes Center : Highnic Group Building, Guangfo Rd., Yanbu, Dali Town, Nanhai District, Foshan City, Guangdong Province, China.
- Mail: sale@imt-pcb.com Fax : (86-757) 85768678 Tel: (86-757) 85728852